

IN THE CLAIMS:

Please amend the claims as follows:

Claims 1 to 13. (Cancelled).

Claim 14. (Cancelled).

Claim 15. (Cancelled).

Claim 16. (Cancelled).

Claim 17. (Cancelled).

Claim 18. (Cancelled).

Claim 19. (Cancelled).

Claim 20. (Cancelled).

Claim 21. (Currently Amended).

A process for the production of a four layer composite material (1, 21) with a plastic layer (4, 24) that has release properties with respect to adhesives consisting of

locating materials producing the release properties within the

plastic layer, wherein a first web (2, 22) is provided in
production of the composite material (1, 21) on one side of which a
layer of adhesive (3, 23) is located, and said adhesive layer is
always coextruded together with the plastic layer (4, 24) with the
release properties, which is in turn bonded to a second web (5,25);
and

wherein said first web and said second web is selected from
the group consisting of paper, metal foil, and non-woven fabric;
and

~~Process according to claim 14, wherein at least providing the~~
first web and the second web simultaneously in a spaced apart
position; and extruding the adhesive layer (3, 23) and the layer
(4, 24) with the release properties are extruded between the two
webs (2, 22 and 5, 25); and forming the bond with the two webs.

Claims 22 to 26. (Cancelled).

Claim 27. (New).

The process according to claim 21,
wherein said first web and said second web is paper.

Claim 28. (New).

The process according to claim 21,
wherein said first web and said second web is metal foil.

Claim 29. (New).

The process according to claim 21,
wherein said first web and said second web is non-woven
fabric.

Claim 30. (New).

A process for the production of a four layer composite
material (1, 21) with a plastic layer (4, 24) that has release
properties with respect to adhesives consisting of

locating materials producing the release properties within the
plastic layer, wherein a first web (2, 22) is provided in
production of the composite material (1, 21) on one side of which a
layer of adhesive (3, 23) is located, and said adhesive layer is
always coextruded together with the plastic layer (4, 24) with the
release properties, which is in turn bonded to a second web (5, 25);
and

wherein said first web and said second web is selected from
the group consisting of paper, metal foil, non-woven fabric, and
plastic; and

providing the first web and the second web simultaneously in a
spaced apart position; and extruding the adhesive layer (3, 23) and
the layer (4, 24) with the release properties between the two webs
(2, 22 and 5, 25); and forming the bond with the two webs.